




# Magnet

## DM 60-31-15

Permanent magnet for magnetic field sensors

### Dimensions



### Technical Data

<b>Ambient conditions</b>	
Ambient temperature	max. 200 °C
<b>Mechanical specifications</b>	
Material	SrFe acc. to ratio 22/14
Dimensions	Height: 15 mm Diameter: 31 mm

Release date: 2020-03-20 Date of issue: 2020-06-29 Filename: 020175\_eng.pdf

Refer to "General Notes Relating to Pepperl+Fuchs Product Information".

Pepperl+Fuchs Group  
www.pepperl-fuchs.com

USA: +1 330 486 0001  
fa-info@us.pepperl-fuchs.com

Germany: +49 621 776 1111  
fa-info@de.pepperl-fuchs.com

Singapore: +65 6779 9091  
fa-info@sg.pepperl-fuchs.com

**PF** PEPPERL+FUCHS

## Technical Features

The hard ferrite magnet consists of strontium ferrite (SrFe). The magnetisation already takes place during the shaping and is thus in imposed axial direction (anisotropic).

The magnetic clamp disk can be screwed onto a surface through a centre hole with a countersunk screw to save space. For fastening, use a M5 countersunk screw made of unmagnetic, non-conducting material, e. g. V2A or brass. The dimensional tolerance usually amounts to  $\pm 0.1$  mm.

Characteristic		Value	
Power product	(W x H) max.	27 ... 32	$\text{kJ/m}^3$
Remanence	$B_r$	380 ... 400	mT
Coercive field strength	$J_{H_C}$	235 ... 290	kA/m
Coercive field strength	$B_{H_C}$	130 ... 275	kA/m
Relative remanent permeability	$\mu_0 \mu_r$	1.45 ... 1.65	mT/ kA/m
Temperature coefficient of the remanence	$\alpha$	-0.20	%/°C
Density	$r$	5.0	$\text{g/cm}^3$